

General Properties

Glass types			Neoceram		
			N-0	N-11	
Color			Transparent	White	
Thermal properties	Thermal expansion coefficient	$\times 10^{-7}/^{\circ}\text{C}$	-50~0°C	-6	0
			0~50°C	-7	2
			30~380°C	-6	8
			30~750°C	-4	12
	Specific heat	J/kg°C	25°C	800	800
	Thermal conductivity	W/m°C	25°C	1.7	1.7
	Max. service temp.	°C	Continuous	750*	800*
		Short term	850*	900*	
Thermal shock resistance	°C	100×100×3mm Plate	800**	600**	
Optical properties	Index of refraction (n_D)		1.541	—	
	Abbe number (v_d)		57	—	
	Stress-optical coeff.	$m\mu/\text{cm}/\text{kg}/\text{cm}^2$	25°C	3.0	—
Mechanical properties	Density	g/cm^3	2.51	2.50	
	Bending strength	MPa	JIS R-1601	160	170
	Vicker's hardness	Hv (0.2)	710	720	
	Young's modulus	GPa	93	87	
Chemical properties	Acid resistance (5% HCl)	mg/cm^2	90°C, 24hrs	0.04	0.24
	Alkali resistance (5% Na_2CO_3)	mg/cm^2	90°C, 24hrs	0.32	0.96
Electrical properties	Volume resistivity ($\text{Log } \rho$)	$\Omega\text{-cm}$	25°C	13	14
			150°C	8	9
			250°C	7	7
			350°C	6	5
	Dielectric constant (ϵ)		1MHz, 25°C	7	6
			2.45GHz, 25°C	—	6.6
	Loss tangent ($\tan \delta$)	$\times 10^{-3}$	1MHz, 25°C	21	3
			2.45GHz, 25°C	—	5.9

* Maximum service temperature: Determination of the maximum service temperature is based on mechanical deformation, and is the temperature of which 100×300×3.8t mm plate specimens (supported to form a 280-mm span) deform by 1mm after 1,000 hours continuous or 24 hours short term heating.

** These figures are only general values derived by a procedure consisting of heated specimens which are then rapidly cooled by plunging them into water. Thermal shock properties of 100°C signify that specimens have been heated to 110°C and plunged into water at 10°C without exhibiting cracking.